LORKOTE 2050 WHITE

ACRYLIC/POLYURETHANE TOPCOAT

DESCRIPTION

Lorkote 2050 is a two-component acrylic polyurethane pigmented topcoat that offers excellent chemical and mar resistance with production friendly dry times. Specifically designed for exterior wood surfaces. The Lorkote 2050 White is anti yellowing and contains UV blocking properties to make it an excellent choice for doors, garage doors, patio furniture and other wood surfaces exposed to exterior environments. It also can be used interior for superior UV protection.

Formaldehyde free

PRODUCT DATA

Color	Clear		
Solids % by Vol	43% ± 2%	**VOC actual**	447 g/L 3.72 lb/gal
Solids %by Wt	58% ± 2%	**Photochemical reactive**	No
Density	1.1	**Flash Point (PM/CC)**	N/A
Viscosity 23°C/73°F #4 Ford	105 ± 2	**Shelf life**	6 months (at 15-25°C/59-77°F)
Gloss(On Black glass @60°)	20, 35,50,90/Available in other gloss level	**Theo-coverage @1 mil dry**	545-550 Sq.Ft/gal 13-14 m^2/L

PREPARATION/APPLICATION

Working Temp >18°C/65°F surface, coating and air

Catalyzation 25% by volume using C 2050 catalyst - 4 parts LORKOTE 2050 to 1 part C 2050 catalyst.

Pot life 4 hours (23°C/74°F)

Reducer Reduce 15-30% by volume with DEDE SL THINNER (slow) or DEDE L THINNER (medium).
To help reduce trapped air, blushing or orange peel, use Retarder LR236 at a maximum of 5%.by volume

Film thickness Min 4 mil wet –Max 6 mil wet

Suggested Sealer ISOLANTE X (Exterior), ISOLANTE I (Interior), FK 48, FK 70

Application

- Color Wood-Stain or tone as desired and dry thoroughly
- Seal-Apply a full coat of ISOLANTE X or ISOLANTE I at 4.0 – 6.0 wet mils. See sealer data sheet for details.
- Allow to dry. Sand with 240, 320 paper, or sponges as required. Topcoat within 8 hours of sanding
- Topcoat – apply LORKOTE 2050 at 4.0 - 6.0 mils wet
- For more depth or build, sand and apply an additional coat.

Surface Preparation Wood surface must be clean, dry, and finish sanded with 180 grit sandpaper Substrate should be clean and free of grease and oil to ensure optimum adhesion and coating performance properties. Moisture content of the wood should be between 6%-8%.

Use Directions Catalyze, adjust viscosity and stir thoroughly before application to avoid variations application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.

App equip. Conventional & HVLP Siphon Feed, Pressure Pot Systems and Airless/Air Assist Equipment.

Tinting Can be tinted up to 10% maximum with universal colorants 844.

Cleanup Clean tools/equipment immediately after use with T750 LORCHEM cleaner gun or a quality lacquer thinner or acetone. Always follow manufacturer's safety recommendations when using any solvent.

Standards This product meets KCMA and CKCA standards when used over recommended LORCHEM sealers.

DRYING TIMES

Method	Drying temperature.	Drying Time (@ 50%RH and thickness @ 4 mil WET)			
Air Drying	23°C/74°F	**Dust free time**	8-12 minutes	**Dry to sand**	2-3 hours
		Dry to touch	45 min-1 hour	**Dry to recoat**	2-3 hours
		Dry to Handle	2-3 hours	**Dry to stack**	24 hours
Force dry	45to 60°C/110-140°F	Minutes			

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Minimum curing temperatures of 23°C/74°F must be maintained throughout curing cycle to achieve the film integrity as stated in product features.

LORKOTE 2050 WHITE

ACRYLIC/POLYURETHANE TOPCOAT

APPLICATION RECOMMENDATIONS

APPLICATION EQUIPMENT SETTINGS

Method of Application	Air Pressure (PSI)	Fluid Pressure (PSI)	TIP size (mm / inch)	Application Viscosity (#FORD 4)	Thickness Film (Mils)
Conventional spray	40-50	08-12	1.8-2/0,070-0,078	18-21	3-5
Airless Spray	10-18	300-600	0,28-0,33/0,011-0,012	18-21	3-5
HVLP	35-45	8-12	1.19-1,39/0,047-0,055	18-21	3-5

Note: All measurements and application equipment settings are based on application at a temperature of 23°C/74°F. Viscosity will vary depending on the temperature of the liquid. The above-mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

SPECIFICATIONS

- For exterior and interior use
- Must be stirred before and during using.
- Must be catalyzed with C 2050 catalyst at a level of 25% by volume. Over catalyzing or using incorrect catalyst may result in blooming, cracking and poor adhesion.
- Store at room temperature (under25°C/ 80° F) after catalyzation. Higher temperatures will reduce the pot life.
- Can be used over recommended LORCHEM sealer. Please contact your representative for system recommendations.
- Maximum cure and chemical resistance are attained after 14 days air-drying.
- Yellowing over white and pastel colors may occur due to the yellowing tendency of the color system (stain, basecoat, etc.), and not to the clear topcoat.
- For maximum life, be sure to coat all sides and edges. If the project is cut or planed at jobsite, the bar edges should be recoated

CAUTIONS

TESTING

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

THESE PRODUCT ARE DESIGNED FOR INDUSTRIAL SHOP APPLICATION AND PROFESSIONAL USE ONLY

Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Please direct any questions or comments to your local representative.

PDS

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling ,preparation and application which are not known or under our control, LORCHEM cannot make any warranties related to the product or the performance of the product. Moreover, we underline the fact that in industrial applications, a tolerance of 5% in the overall results is considered normal and is not caused by the quality of the product.

CONTACT

PH: +1(450)424-4000
F: +1(450) 424-9134
http://www.lorchemintl.com

LORCHEM INTERNATIONAL
150,Rue Aimé-Vincent Vaudreuil, Dorion,
QC J7V5V5